

DEVELOPMENT OF COIR FIBER REINFORCED COMPOSITE MATERIAL

A Thesis
by

Md. Rakib Hossain	ME2202027278
Md. Arafat Azad Ashik	ME2202027294
Md. Shopon Ali	ME2202027313
Rashel Mahmud	ME2202027248
Milon Kumar Barman	ME2202027315



DEPARTMENT OF MECHANICAL ENGINEERING
SONARGAON UNIVERSITY (SU)

JANUARY, 2026

DEVELOPMENT OF COIR FIBER REINFORCED COMPOSITE MATERIAL

A thesis

By

Md. Rakib Hossain	ME2202027278
Md. Arafat Azad Ashik	ME2202027294
Md. Shopon Ali	ME2202027313
Rashel Mahmud	ME2202027248
Milon Kumar Barman	ME2202027315

Supervisor: Shahinur Rahman

Assistant Professor

Submitted to the
DEPARTMENT OF MECHANICAL ENGINEERING
SONARGAON UNIVERSITY (SU)
In partial fulfillment of the requirements for the award of the degree
of
BACHELOR OF SCIENCE IN MECHANICAL ENGINEERING

JANUARY, 2026

ACKNOWLEDGEMENT

First, we started in the name of almighty Allah. This thesis is accomplished under the supervision of **Shahinur Rahman, Assistant Professor** Department of Mechanical, Sonargaon University. It is a great pleasure to acknowledge our profound gratitude and respect to our supervisor for this consistent guidance, encouragement, helpful suggestion, constructive criticism and endless patience through the progress of this work. The successful completion of this thesis would not have been possible without his persistent motivation and continuous guidance.

The authors are also grateful to **Prof. Md. Mostofa Hossain, Professor**, Head of the Department of Mechanical Engineering and all respect teachers of the Mechanical Engineering Department for their co-operation and significant help for completing the thesis work successfully.

[Authors]

Md. Rakib Hossain
ME2202027278

Md. Arafat Azad Ashik
ME2202027294

Md. Shopon Ali
ME2202027313

Rashel Mahmud
ME2202027248

Milon Kumar Barman
ME2202027315

Abstract

This research focuses on the mechanical properties and performance analysis of coir fiber and glass fiber reinforced epoxy composites, particularly evaluating the effect of fiber orientation under various mechanical tests. Hybrid composites were fabricated using coir fibers oriented at 45°, 60°, and 90°, combined with glass fibers in an epoxy matrix. Mechanical testing included hardness and impact tests to understand the influence of fiber orientation on the overall properties of the composites. The results demonstrated a significant correlation between fiber orientation and the mechanical behavior of the composites. The 45° coir fiber orientation exhibited superior impact strength, attributed to its ability to absorb and dissipate energy more effectively under dynamic loading conditions. On the other hand, the 45° orientation resulted in higher hardness values, indicating better resistance to localized deformation. The 45° orientation showed balanced performance but did not surpass the other configurations in either hardness or impact strength. This study highlights the importance of fiber orientation in designing hybrid composites to achieve desired mechanical properties. By optimizing orientation, it is possible to tailor the composite for specific applications, such as automotive, aerospace, and structural components, where lightweight materials with enhanced strength and durability are crucial. These findings provide valuable insights for future development of sustainable, high-performance composite materials.

Table of Contents

Acknowledgement	iii
Abstract	iv
Table of Contents	vi
Table of Figure	vii
List of Table	viii
CHAPTER-1 : INTRODUCTION	
1.1 Introduction	1
1.2 Literature Review	2
1.3 Objective	3
CHAPTER 2 : MATERIALS AND PROPERTIES	
2.1 Material Used	4
2.2 Material Properties	5
2.3 Test Specimen Preparation	7
CHAPTER-3 : FABRICATION OF COMPOSITES	
3.1 Introduction	8
3.2 Mold Preparation	8
3.3 Layering Configuration	8
3.4 Resin Application	9
3.5 Compression and Curing	9
CHAPTER-4 : EXPERIMENTAL PROCEDURE	
4.1 Universal Testing Machine	10
CHAPTER-5 : RESULT AND DISCUSSION	
5.1 Hardness test Results	14
5.2 Impact Test Results	17
5.3 Bending Test Results	20
5.4 Advantages	29

CHAPTER-6 : CONCLUSION AND FUTURE SCOPE

6.1 Conclusion	23
6.2 Future Scope	25
References	26

List of Figures

Figure no	Figure name	Page no
2.1	Glass Fiber & Coir Fiber	4
2.2	Cutting The Specimen	7
3.1	Layering	9
4.1	Bending Test Machine	10
4.2	Hardness Test Machine	11
4.3	Impact Test Machine	12
5.1	Hardness Test Specimens After Testing	14
5.2	Graph Chart hardness Test	15
5.3	Line Graph of Hardness Test	16
5.4	Impact test specimens showing fracture patterns after testing	17
5.5	Graph Chart of Impact Test	18
5.6	Line Graph of Impact Test	19
5.7	Bending Test Specimens after Testing	20
5.8	Graph Chart of Bending Test	21
5.9	Line Graph of Bending Test	22

List of Table

Table no	Table name	Page no
5.1	Data Table of Hardness Test	15
5.2	Data Table of Impact Test	18
5.3	Data Table of Banding Test	21
6.1	Coir Fiber Reinforced Composite vs Industrial Materials	24
6.2	Comparative Applications of Coir Fiber Reinforced Composites	25

CHAPTER 1

INTRODUCTION

1.1 Introduction

The increasing global demand for lightweight, high-strength, and sustainable materials has driven significant advancements in composite technology. Composite materials have become a cornerstone in industries like automotive, aerospace, and construction due to their ability to deliver superior mechanical performance while reducing weight. Among natural fibers, Coir has garnered significant attention for its renewable nature, biodegradability, and excellent tensile strength. However, its standalone application is often limited due to its relatively lower impact resistance, hardness, and durability compared to synthetic fibers [1], [2].

To address these limitations, hybrid composites that combine natural fibers like Coir with synthetic fibers such as glass have emerged as an effective solution. Glass fibers, renowned for their exceptional strength, stiffness, and impact resistance, complement the mechanical properties of coir fibers, enabling the development of composites that balance performance and sustainability [3], [4]. When combined within an epoxy resin matrix, these materials form hybrid composites that exhibit enhanced strength, durability, and energy absorption properties [5].

One critical factor influencing the performance of these hybrid composites is fiber orientation. The anisotropic behavior of composites, stemming from the alignment of fibers, affects key mechanical properties, including impact resistance, hardness, and loadbearing capacity. Proper alignment and hybridization of fibers can result in materials tailored to specific industrial applications, offering optimized performance and weight reduction [6], [7]. This research investigates the mechanical properties and performance of hybrid epoxy composites reinforced with coir and glass fibers, with a specific focus on the impact of coir fiber orientation (45°, 60°, and 90°). Through bending, hardness, and impact tests, this study aims to optimize fiber orientation to advance the development of sustainable, high-performance materials for various industrial applications. By leveraging

the complementary properties of coir and glass fibers, this work contributes to the growing field of bio-based hybrid composites, addressing environmental concerns while meeting engineering demands.

1.2 Literature Review

Fiber-reinforced composites have become a key area of research due to their ability to combine lightweight structures with excellent mechanical properties. Hybrid composites, integrating both natural and synthetic fibers, are particularly promising as they blend performance with sustainability. This section provides an overview of prior studies focusing on the hardness and impact performance of fiber-reinforced composites, with a particular emphasis on hybrid configurations.

Natural Fibers in Composites

Natural fibers, such as coir, have gained prominence for their environmental benefits, including biodegradability, renewability, and low cost. Coir fibers, in particular, are widely used in polymer matrices due to their availability, high tensile strength, and low density. However, their mechanical properties, such as impact resistance and hardness, are relatively inferior to those of synthetic fibers, limiting their standalone application in highperformance scenarios [1], [8].

Synthetic Fibers in Composites

Synthetic fibers, such as glass fibers, are widely utilized in reinforced composites for their superior mechanical properties. Glass fibers exhibit high tensile strength, stiffness, and impact resistance, making them suitable for applications demanding enhanced durability and performance. However, the environmental impact and non-biodegradable nature of glass fibers remain significant challenges [2], [9].

Hybrid Composites and Performance

The hybridization of natural and synthetic fibers combines the strengths of both materials, resulting in composites with improved mechanical performance and sustainability. Hybrid composites that integrate coir and glass fibers have shown improved hardness and impact resistance compared to composites made from either fiber alone [3], [4], [10]. Fiber orientation also plays a crucial role in determining composite

performance. For instance, unidirectional fibers may enhance hardness along the load direction, while bidirectional or random orientations improve toughness and impact resistance [5], [11].

Mechanical Testing of Hybrid Composites

Hardness and impact tests are essential for evaluating the surface durability and energy absorption capacity of composites. Studies have demonstrated that the inclusion of glass fibers significantly enhances hardness, while hybrid configurations with natural fibers improve energy absorption. For example, composites with bidirectional fiber alignment exhibit better impact resistance than those with unidirectional configurations, underscoring the importance of fiber orientation in hybrid composites [3], [6], [12].

This research builds on existing literature to examine the combined effects of jute and glass fibers in hybrid epoxy composites. By focusing on fiber orientation and its impact on hardness and impact resistance, this study aims to provide practical insights into optimizing hybrid composites for lightweight, durable, and sustainable applications.

1.3 Objectives

- To evaluate the influence of coir fiber orientation (45° , 60° , and 90°) on the bending test, hardness of hybrid epoxy composites and impact resistance.
- To analyze the role of multidirectional glass fibers in reinforcing the mechanical properties of hybrid composites.
- To develop a cost-effective, lightweight, and eco-friendly hybrid composite suitable for engineering applications.
- To explore the potential applications of coir-glass composites in structural, automotive, aerospace, and construction sectors.
- To contribute to sustainable material development by partially replacing synthetic fibers with natural jute fibers.

CHAPTER 2

MATERIALS AND PROPERTIES

2.1 Material Used

The materials used in this study include:

- **Coir Fiber:** Natural coir fabric of 300 gsm was used as reinforcement.
- **Glass Fiber:** Woven glass fiber fabric of 400 gsm was utilized for its superior mechanical properties.
- **Epoxy Resin and Hardener:** A-grade epoxy resin and its corresponding hardener were employed as the matrix material to ensure strong bonding and mechanical stability.
- **Additional Materials:** A release film and mold plates were used during the fabrication process to facilitate smooth curing and easy removal of composite samples.



Figure: 2.1 Glass Fiber & Coir Fiber

2.2 Material Properties

Coir Fiber

Coir is a natural fiber known for its eco-friendly characteristics.

- **Physical Properties**

- ✓ **Density:** $\sim 1.3\text{--}1.46\text{ g/cm}^3$ (low compared to synthetic fibers).
- ✓ **Tensile Strength:** $\sim 250\text{--}350\text{ MPa}$.
- ✓ **Young's Modulus:** $\sim 20\text{--}55\text{ GPa}$.
- ✓ **Elongation at Break:** $\sim 1.5\text{--}1.8\%$.

- **Mechanical Properties**

- ✓ Low tensile strength compared to synthetic fibers like glass.
- ✓ Moderate impact resistance.
- ✓ Good energy absorption due to its toughness

- **Thermal Properties**

- ✓ Thermal degradation starts at $\sim 200\text{--}230^\circ\text{C}$.
- ✓ Low thermal conductivity, making it a good insulator.

- **Chemical Properties**

- ✓ **Hydrophilic Nature:** High moisture absorption (8–12%), which can lead to swelling or degradation in wet environments.
- ✓ Resistance to weak acids but prone to degradation in alkaline conditions.

- **Environmental Properties**

- ✓ Biodegradable and renewable.
- ✓ Environmentally sustainable with low carbon emissions during production.

Glass Fiber

Glass fibers are synthetic fibers made primarily from silica and are widely used in reinforced composites.

● **Physical Properties**

- ✓ **Density:** $\sim 2.5\text{--}2.6\text{ g/cm}^3$ (higher than jute).
- ✓ **Tensile Strength:** $\sim 1,200\text{--}2,000\text{ MPa}$.
- ✓ **Young's Modulus:** $\sim 70\text{--}80\text{ GPa}$.
- ✓ **Elongation at Break:** $\sim 2.5\text{--}4.8\%$.

● **Mechanical Properties**

- ✓ High tensile and compressive strength.
- ✓ Excellent stiffness and rigidity.
- ✓ Good impact resistance compared to natural fibers.

● **Thermal Properties**

- ✓ Can withstand high temperatures (up to 800°C for E-glass fibers).
- ✓ Low thermal expansion coefficient.

● **Chemical Properties**

- ✓ **Hydrophobic Nature:** Resistant to water and moisture.
- ✓ Chemically inert to acids and bases, making it highly durable in harsh environments.

● **Environmental Properties**

- ✓ Non-biodegradable.
- ✓ Energy-intensive production process.
- ✓ Recycling is possible but not as environmentally sustainable as natural fibers.

2.3 Test Specimen Preparation

After curing, the 11.81" × 11.81" composite plates were removed from the mold and trimmed to ensure uniformity. Specimens for mechanical testing were prepared as follows:

- **Bending Test:** The accuracy of results depends heavily on how well the test specimen is prepared. Standards such as ASTM D79.
- **Hardness Test:** Samples were tested directly from the 11.81" × 11.81" plates for surface hardness using a durometer.
- **Impact Test:** Square specimens were cut to the required dimensions based on ASTM D256 standards to evaluate the impact resistance.

Each sample was carefully inspected for defects, such as voids or delamination, to ensure the reliability and consistency of test results. Specimens were stored in controlled conditions to prevent moisture absorption before conducting the tests.



Figure: 2.2 Cutting the Specimen

CHAPTER 3

FABRICATION OF COMPOSITES

3.1 Introduction

The composite samples were fabricated using the hand lay-up method followed by compression molding. The following steps outline the fabrication process in detail:

3.2 Mold Preparation

A mold of 11.81" × 11.81" dimensions was prepared and lined with a release film to prevent the composite from adhering to the mold surface. The release film also ensures ease of demolding and avoids surface defects on the composite. Proper cleaning and waxing of the mold surface were carried out before applying the release film to enhance its effectiveness.

3.3 Layering Configuration

The composite samples consisted of four layers, arranged in the following sequence: coir fiber – glass fiber – coir fiber – glass fiber. This specific sequence ensures a balanced distribution of the reinforcing fibers and provides a hybrid structure combining the properties of both coir and glass fibers. For each sample, the coir fiber layers were oriented at specific angles to investigate the effect of fiber orientation on mechanical properties:

- **Sample 1: Coir** fibers oriented at 45°
- **Sample 2: Coir** fibers oriented at 60°
- **Sample 3: Coir** fibers oriented at 90°

This variation in orientation is intended to analyze the anisotropic behavior of the composites under mechanical loading.




Figure: 3.1 Layering

3.4 Resin Application

A high-grade epoxy resin, known for its excellent adhesion and mechanical properties, was used as the matrix material. The resin was mixed with a hardener in a 3:1 ratio by weight, following the manufacturer's guidelines to achieve optimal curing and cross-linking. The mixture was stirred thoroughly to ensure homogeneity and to prevent unmixed regions that could weaken the composite. The resin-hardener mixture was evenly applied to each layer using a roller to ensure complete impregnation of the fibers. Special attention was given to eliminate air bubbles during the application process, as trapped air can lead to voids and reduce the mechanical strength of the composite.

3.5 Compression and Curing

After stacking and impregnating the layers, the composite laminate was placed in the mold and subjected to uniform pressure using a compression molding machine. This step ensured proper compaction of the layers, reduced void content, and enhanced the fiber-matrix bonding. The composite was allowed to cure at room temperature for 24 hours to achieve initial hardening. The detailed fabrication process ensures the production of high-quality composite samples, suitable for subsequent mechanical testing and performance analysis.

CHAPTER 4

EXPERIMENTAL PROCEDURE

4.1 Universal testing Machine (UTM)

A Universal Testing Machine (UTM) is a versatile device used to evaluate the mechanical properties of materials under tension, compression, and bending. It typically features a robust frame, load capacities ranging from 1 kN to 2000 kN, and high-precision load cells. The machine includes a motorized crosshead with adjustable speeds (0.1–500 mm/min), extensometers for accurate strain measurement, and digital or computer-based control systems for data acquisition and analysis. Various grips and fixtures accommodate different material shapes and test standards (ASTM, ISO). UTMs are essential in quality control, research, and development for testing metals, polymers, composites, and construction materials.



Figure: 4.1 Bending Test Machine

Mechanical Test Performed

Bending Test

The Shore B hardness of the composite samples was measured using a durometer as per ASTM D79 standards. Samples were prepared with dimensions of $300 \times 300 \times 4.5 \text{ mm}^3$. Bending Test measures a material's flexural strength, stiffness, and ductility, showing how much it can bend before breaking. A defect-free specimen is prepared and placed on

a three- or four-point bending machine. Load is applied until failure, recording maximum load, deflection, stress, and strain to assess material quality

Hardness Test Machine :

A Hardness Test Machine is designed to measure a material's resistance to deformation through indentation. Common types include Rockwell, Brinell, and Vickers testers. Specifications vary by type but typically include a load range of 1 kgf to 3000 kgf, depending on the test method. Indenters may be steel balls, diamond cones, or pyramids. Machines feature manual or motorized loading, digital or analog readouts, and precision depth or optical measurement systems. Advanced models include automated test cycles, data storage, and software integration. They are suitable for testing metals, alloys, plastics, and ceramics in quality control, research, and industrial applications.



Figure: 4.2 Hardness Test Machine

Mechanical Test Performed

Hardness Test

The Shore B hardness of the composite samples was measured using a durometer as per ASTM D2240 standards. Samples were prepared with dimensions of $150 \times 150 \times 4.5$ mm³. In addition, the Rockwell hardness test was conducted using a Rockwell B steel ball indenter under a 100 kg load, which is suitable for softer materials like the composites tested. The hardness values were recorded as numerical readings, representing the material's resistance to deformation under the applied load. Higher

values indicated greater hardness. All measurements were performed under controlled environmental conditions to ensure accuracy and repeatability [6].

Impact Test Machine

An Impact Test Machine is used to determine a material's toughness by measuring its ability to absorb energy during sudden impact. Common types include Charpy and Izod impact testers. Specifications typically include a pendulum with energy capacity ranging from 150 J to 750 J, digital or analog energy indicators, and support for test temperatures from ambient to sub-zero (using a cooling chamber). The machine consists of a heavy pendulum, specimen support (horizontal for Charpy, vertical for Izod), and precise measurement scales. Materials are notched before testing to concentrate stress. Impact testers are essential in quality control, especially for metals and engineering plastics.



Figure: 4.3 Impact Test Machine

Mechanical Test Performed

Impact Test

The impact resistance of the composites was evaluated using the Charpy impact test as per ASTM D256 standards. Square specimens, $50 \times 6 \times 4.5 \text{ mm}^3$ in dimension, were prepared and visually inspected for defects such as voids or delamination to ensure consistency. During testing, specimens were subjected to a pendulum impact until

fracture occurred. The energy absorbed by the material during fracture was recorded to determine its toughness and yield strength. This test also provided insights into the effect of strain rate on the material's fracture behavior and ductility. Specimens were stored in a controlled environment to prevent moisture absorption before testing.

Testing Orientations

The mechanical tests were conducted on composite samples with varying coir fiber orientations to evaluate the influence of fiber alignment on mechanical performance.

- **Sample 1:** Coir fibers oriented at 45°.
- **Sample 2:** Coir fibers oriented at 60°.
- **Sample 3:** Coir fibers oriented at 90°

For each sample, the coir fiber sequence (glass fiber-coir-glass fiber-coir-glass fiber) and the orientation of the coir fibers were maintained consistently during fabrication. This allowed for a comparative analysis of the effect of fiber orientation on hardness and impact resistance.

All tests were conducted in a controlled environment to ensure reliability and reproducibility of results.

CHAPTER 5

RESULTS AND DISCUSSION

5.1 Hardness Test Results

The hardness test results for the composite samples with varying coir fiber orientations (45°, 60°, and 90°) are summarized below:

- **45° Orientation:** The samples displayed hardness values of **80,88** and **93 HRL** showing consistent surface resistance.
- **60° Orientation:** Hardness values were slightly higher, with readings of **70,76** and **81 HRL**
- . The improved performance at 45° indicates better stress distribution due to the alignment of fibers.
- **90° Orientation:** Samples exhibited hardness values ranging from **68,75,80 HRL** with variability likely caused by inconsistent fiber alignment at this orientation.

The results demonstrate that fiber orientation significantly impacts the hardness of the composite. The 45° orientation yielded the most consistent and higher hardness values, likely due to the balanced contribution of both coir and glass fibers.




Figure: 5.1 Hardness test specimens after testing


Data Table for Hardness Test

Table: 5.1 Data Table of Hardness Test

Specimen No.	1	2	3	Average
45°(HRL)	80	88	93	87
60°(HRL)	70	76	81	75.66
90°(HRL)	68	75	80	74.33



Graph Chart : 5.2 Graph Chart of Hardness Test



Line Graph: 5.3 Line Graph of Hardness Test

- Line Graph shows the hardness test result at 45°, 60° and 90° .

Comparison

- At 45°, our results and the reference results show high hardness, with our configuration showing slightly better performance (87)
- At 60° (our result) vs. 90° (reference), the hardness is comparable, with 90° yielding slightly lower values (75.66).
- 90° orientation provides better hardness (74.33) than 0° orientation (~10).

5.2 Impact Test Results

The impact resistance of the composite samples was evaluated based on the energy absorbed during testing, with the results categorized by fiber orientation:

- **45° Orientation:** Impact energies recorded were **6 ft-lb, 8 ft-lb**.
- **60° Orientation:** Samples exhibited higher energy absorption, with values of **5 ft-lb, 6 ft-lb**.
- This orientation provided better impact resistance, likely due to optimized load transfer between fibers.
- **90° Orientation:** The samples showed varying energy absorption, with values of **4.5 ft-lb, 5 ft-lb**. Despite higher absorption in some cases, variability suggests potential misalignment or uneven stress distribution at this angle.



Figure: 5.4 Impact test specimens showing fracture patterns after testing


The results indicate that the 45° fiber orientation provides superior and consistent impact resistance, emphasizing its suitability for applications requiring enhanced toughness. Comparatively, the 60° and 90° orientations demonstrated lower performance, with variability in energy absorption likely due to non-optimal fiber alignment.

In summary, both the hardness and impact test results underline the critical influence of fiber orientation on the mechanical performance of jute and glass fiber-reinforced epoxy composites. The 45° orientation emerged as the most effective configuration for achieving a balance of surface hardness and impact resistance.


Data Table for Impact Test

Table: 5.2 Data Table of Impact Test

Specimen No.	1	2	Average
45° energy (ft.lb)	6	8	7
60° energy (ft.lb)	5	6	5.5
90° energy (ft.lb)	4.5	5	4.75



Graph Chart : 5.5 Graph Chart of Impact Test



Line Graph: 5.6 Line Graph of Impact Test

- Line graph shows the impact test result at 45° , 60° and 90°

Comparison:

- At 45°, both your results and the reference results demonstrate superior impact resistance, with your results slightly outperforming (7 ft-lb vs. 6 ft-lb).
- 90° orientation (4.75 ft-lb) is slightly lower.
- 60° orientation (5.5 ft-lb) performs slightly better than 0° (5 ft-lb).

5.3 Bending Test Result

The bending strength of the composite samples was evaluated under three-point bending, with the results categorized by fiber orientation:

- **45° Orientation:** Samples exhibited the highest and most consistent bending strength, with values of 1.25 MPa, 1.75 MPa, and 2 MPa. This orientation provided superior load distribution and effective stress transfer, resulting in enhanced resistance against bending failure.
- **60° Orientation:** The recorded strengths were moderate, with values of 1.25 MPa, 1.5 MPa, and 1.75 MPa. Although performance was relatively stable, the results indicate slightly reduced bonding efficiency compared to 45° orientation.
- **90° Orientation:** Samples showed the lowest bending strength, with values of 1.5 MPa,

1.4 MPa, and 1.25 MPa. This orientation displayed weak resistance due to poor load transfer along the fiber direction, making it the least effective configuration under bending loads.




Figure: 5.7 Bending Test Specimens After Testing

The findings indicate that the 45° fiber orientation demonstrates superior bending resistance, making it highly suitable for structural applications requiring strength and reliability. Comparatively, the 60° and 90° orientations exhibited weaker performance, which may be attributed to less effective stress transfer and fiber alignment


Data Table for Bending Test

Table: 5.3 Data Table of Bending Test

Specimen No.	1	2	3	Avarage
45° Load(Mpa)	1.25	1.75	2	1.7
60° Load(Mpa)	1.25	1.5	1.75	1.5
90° Load(Mpa)	1.5	1.4	1.25	1.4



Graph Chart : 5.8 Graph Chart of Bending Test



Line Graph: 5.9 Line Graph of Bending Test

- Line graph shows the Bending test result at 45°, 60° and 90°

Comparison

- At 45°, both your results and the reference results demonstrate superior impact resistance, with your results slightly better performing (1.7 vs. 1.25 Mpa).
- 90° orientation (1.3 Mpa) is slightly lower.
- 60° orientation (1.5 Mpa) performs slightly better than 0° (1.4 Mpa).

CHAPTER 6

CONCLUSIONS AND FUTURE SCOPE

6.1 Conclusion

This study evaluated the mechanical performance of coir and glass fiber-reinforced epoxy composites by conducting hardness and impact tests on samples with different coir fiber orientations (45°, 60°, and 90°). The key findings are as follows:

Bending Test:

The 45° orientation demonstrated the highest and most consistent bending strength among the three configurations (average: 1.7 MPa), outperforming both the 60° and 90° orientations (average: 1.5 MPa and 1.4 MPa, respectively). This indicates superior load distribution and effective stress transfer at 45°, while the lower performance at 60° and 90° suggests reduced bonding efficiency and weaker resistance to bending loads.

Hardness Test:

The 45° orientation exhibited the highest hardness values among the three configurations (average: 87), clearly outperforming both the 60° and 90° orientations (average: 75.66 and 74.33, respectively). This indicates that the 45° fiber alignment provides superior resistance to surface indentation, while the relatively lower hardness at 60° and 90° suggests less effective stress distribution.

Impact Test:

The 45° orientation exhibited superior impact resistance, absorbing the highest energy during testing (average: 7). It outperformed the 60° (average: 5.5) and 90° (average: 4.75) orientations, confirming its effectiveness in optimizing energy absorption. The decreasing trend from 45° to 90° indicates that fiber orientation plays a vital role in impact strength, with more favorable energy absorption observed at lower angles. These results emphasize the significance of orientation in tailoring mechanical properties, with the 45° orientation emerging as the optimal configuration for maximizing impact resistance.

Comparative Table: Coir Fiber Reinforced Composite vs Industrial Materials

Comparative Table: 6.1 Coir Fiber Reinforced Composite vs Industrial Materials

Property	Composite (45°, Best Orientation)	Typical Industrial Materials	Comparative Remarks & Potential Alternatives
Hardness (Rockwell)	80-95 HRL	<ul style="list-style-type: none"> - Softwood: 5–15 HRL - Hardwood: 20–40 HRL - Unreinforced Epoxy: 10–20 HRL - ABS / Nylon Plastics: 15–30 HRL - Aluminum (annealed): ~15 HRB (\approx25–30 HRL) - Mild Steel: 60–100 HRB 	Comparable to softwood, epoxy, and low-hardness plastics; much lower than metals. Suitable alternative to woodbased boards and some plastic housings.
Impact Resistance (ft-lb)	~6–8	<ul style="list-style-type: none"> - Wood (pine): ~2–5 ft-lb - Epoxy resin: ~1–2 ft-lb - ABS plastic: ~3–7 ft-lb - Aluminum alloy: ~20–30 ft-lb - Steel: 50+ ft-lb 	Comparable to wood and epoxy, and close to ABS plastics; far below metals. Best suited for lightweight, low-impact panels or casings.
Bending Strength (MPa)	1.25–2.0 MPa	<ul style="list-style-type: none"> - Wood (pine): ~40–80 MPa - Plywood: ~30–60 MPa - Epoxy resin: ~20–50 MPa - ABS plastic: ~60–110 MPa - Glass fiber composites: 200–500 MPa - Aluminum: 150–300 MPa - Steel: 250–600 MPa 	Much lower than wood, plastics, metals, and reinforced composites. Not suitable for structural or load-bearing parts. Could be used in non-structural covers, partitions, or panels.

Improvement avenues: To make this composite more competitive, you might try increasing fiber volume fraction, optimizing fiber alignment, better bonding at fiber–matrix interface, perhaps adding fillers (ceramic, harder particles), or post-treatment (surface coatings, hard coatings).

6.2 Future Scope

This research lays the foundation for further exploration of hybrid fiber composites.

Future work can focus on:

- **Additional Mechanical Tests:** Evaluating tensile, flexural, and fatigue properties to gain a comprehensive understanding of the composite's mechanical behavior.
- **Effect of Fiber Volume Fraction:** Investigating how varying the proportions of coir and glass fibers influences mechanical properties.
- **Moisture and Environmental Testing:** Assessing the performance of composites under different environmental conditions, such as humidity, temperature, and UV exposure.
- **Alternate Resin Systems:** Exploring the use of bio-based or modified epoxy resins to further improve the sustainability of the composite.
- **Optimization of Fabrication Techniques:** Studying advanced manufacturing methods, such as vacuum bagging or resin infusion, to minimize voids and enhance mechanical properties. These future directions will enable the development of optimized hybrid composites for applications in automotive, aerospace, and structural industries, ensuring sustainability without compromising performance.

Comparative Applications of Coir Fiber Reinforced Composites:

Comparative Table: 6.2 Comparative Applications of Coir Fiber Reinforced Composites

Sector	Conventional Materials	Coir Glass Hybrid Composite (Alternative)	Advantages
Automotive	Steel, Aluminum, Pure Glass Fiber Composites	Interior panels, dashboards, nonload structural parts	Lightweight, cost-effective, fuel efficiency
Construction	Steel rods, Plywood, Cement boards	Wall panels, boards, partition sheets	Eco-friendly, moderate strength, reduced weight
Aerospace	Carbon/Glass Fiber Composites	Interior panels, insulation, secondary components	Weight reduction, sustainable, cheaper
Marine	Glass Fiber Laminates	Boat interior panels, flooring, covers	Good strength, water resistance, lower cost
Furniture & Sports	Wood, Plastics, Pure Synthetic Composites	Chair frames, helmets, rackets, sports boards	Lightweight, durable, ecofriendly alternative

REFERENCES

- [1] K. L. Pickering, M. G. Aruan Efendy, and T. M. Le, "A review of recent developments in natural fiber composites and their mechanical performance," *Composites Part A: Applied Science and Manufacturing*, vol. 83, pp. 98–112, 2016.
- [2] T. P. Sathishkumar, S. Satheeshkumar, and J. Naveen, "Glass fiber-reinforced polymer composites – A review," *Journal of Reinforced Plastics and Composites*, vol. 33, no. 13, pp. 1258–1275, 2014.
- [3] M. Jawaid and H. P. S. Abdul Khalil, "Cellulosic/synthetic fiber reinforced polymer hybrid composites: A review," *Carbohydrate Polymers*, vol. 86, no. 1, pp. 1– 18, 2011.
- [4] M. R. Sanjay, S. Siengchin, and M. Jawaid, "Comprehensive review on durable biocomposites: Hybridization of synthetic fibers and bio-fibers for composites," *Journal of Materials Science*, vol. 55, no. 19, pp. 7293–7320, 2020.
- [5] P. K. Mallick, *Fiber-reinforced composites: Materials, manufacturing, and design*. CRC Press, 2007.
- [6] R. F. Gibson, *Principles of composite material mechanics*. CRC Press, 2016.
- [7] A. Gholampour and M. P. Shanks, "The influence of natural fiber properties on composite performance," *Polymers*, vol. 11, no. 7, pp. 1134, 2019.
- [8] R. S. Chavan, "Natural fibers as sustainable reinforcements in composites: A review," *Journal of Cleaner Production*, vol. 258, pp. 120-131, 2020.
- [9] S. Wang, M. L. Zheng, and D. Y. Zhang, "Performance analysis of glass fiber composites for engineering applications," *Materials Science Forum*, vol. 1003, pp. 273278, 2020.
- [10] S. Mukherjee and J. O. Reddy, "A review on novel eco-friendly hybrid composites," *Renewable and Sustainable Energy Reviews*, vol. 82, pp. 2903-2915, 2018.
- [11] A. K. Bledzki and J. Gassan, "Composites reinforced with cellulose-based fibers," *Progress in Polymer Science*, vol. 24, no. 2, pp. 221-274, 1999.
- [12] F. Sarasini, J. Tirillò, and L. Ferrante, "Mechanical and thermal performance of hybrid composites: Natural and synthetic fiber combinations," *Journal of Applied Polymer Science*, vol. 137, no. 14, pp. 47893, 2020.
- [13] M. N. Jahir, R. Mustak, A. K. Debnath, and P. D. Nath, "Orientation effect of jute/glass fiber reinforced composite on mechanical properties, journal of Engineering

Research, pp. 05, Year 2021.

[14] KK Chawla, Composite Materials: Science and Engineering, 2nd Edition, Springer, New York, 1998.

[15] F Gao, L Boniface and SL Ogin, Damage Accumulation in Woven Fabric CFRP Laminates, Composite Science and Technology, 1999.

[16] HMS Belmonte, CIC Manger and SL Ogin, Characterisation and modelling of the notch tensile fracture of woven quasi-isotropic GFRP laminates. Composite Science and Technology, 2001.

[17] G Kalaprasad and S Thomas, Hybrid Fiber Reinforced Polymer Composites, International Plastics Engineering and Technology, 1995.

[18] M Jawaid, HPSA Khalil, A Hassan and R Dungani and A Hadiyane, Effect of Coir Fiber Loading on Tensile and Dynamic Mechanical Properties of Oil Palm Epoxy Composites, Composites, 2013.

[19] IK Verma, SR Anantha Krishnan and S Krishnamoorthy, Composites of Glass/Modified Coir Fabric and Unsaturated Polyester Resin, Composites, 1989.

[20] S Dixit and P Verma, The effect of hybridization on Mechanical Behavior of Coir/Sisal / Coir Fibers Reinforced Polyester Composite Materials, Research Journal of Chemical Sciences, 2012.

[21] KS Ahmed, S Vijayarangan and ACB Naidu, Elastic properties, Notched Strength and Fracture Criterion in Unsaturated Woven Coir-Glass Fabric Reinforced Polyester Hybrid Composite, Materials and Design, 2007.

[22] MM Thwe and K Liao, Characterization of Bamboo-Glass Fiber Reinforced Polymer Matrix Hybrid Composite, Journal of Materials Science Letters, 2000.

[23] KS Ahmed and S Vijayarangan, Tensile, Flexural and Inter-Laminar Shear Properties of Woven Jute and Jute Glass Fabric Reinforced Polyester Composites, Journal of Materials Processing Technology, 2008.

[24] S Mishra, AK Mohanty, LT Drzal, M Misra, S Parija, SK Nayak and SS Tripathy, Studies on Mechanical Performance of Biofiber/Glass Reinforced Polyester Hybrid Composites, Composites Science and Technology, 2003.

[25] KS Pandya, C Veerajuru and NK Naik, Hybrid Composites Made of Carbon and Glass Woven Fabrics Under Quasi-Static Loading, Materials and Design, 2011.

[26] MS Sreekala, J George, MG Kumaran and S Thomas, The Mechanical Performance of Hybrid Phenol-Formaldehyde-Based Composites Reinforced with Glass and Oil Palm Fibers, Composites Science and Technology, 2002.

- [27] R Velmurugan and V Manikandan, Mechanical Properties of Palmyra/Glass Fiber Hybrid Composites, Composites Part A: Applied Science and Manufacturing, 2007.
- [28] G Goud and R Rao, Mechanical and Electrical Performance of Roystonea regia/Glass Fiber Reinforced Epoxy Hybrid Composites, Bulletin of Materials Science, 2012.
- [29] LA Pothan, CN George, MJ John and S Thomas, Dynamic mechanical and dielectric behavior of banana-glass hybrid fiber reinforced polyester composites, Journal of Reinforced Plastics and Composites, 2010.
- [30] M Thiruchitrambalam, A Alavudeen, A Athijayamani, N Venkateshwaran and AE Perumal, Improving Mechanical Properties of Banana/Kenaf Polyester Hybrid Composites Using Sodium Lauryl Sulphate Treatment, Materials Physics and Mechanics, 2009.
- [31] LX Zhong, Fu Yu, XS Zhou and HS Zhan, Effect of Surface Micro-Fibrillation of Sisal Fiber on the Mechanical Properties of Sisal/Aramid Fiber Hybrid Composites, Composites: Part A, 2011.
- [32] CG Sanjeevamurthy and GR Srinivas, Sisal/Coconut Coir Natural Fibers – Epoxy Composites: Water Absorption and Mechanical Properties, International Journal of Engineering and Innovative Technology, 2012.
- [33] N Venkateshwaran, A ElayaPerumal, A Alavudeen and M Thiruchitrambalam, Mechanical and Water Absorption Behavior of Banana/Sisal Reinforced Hybrid Composites, Materials and Design, 2011.
- [34] C Girisha Sanjeevamurthy and Gunti Rangasrinivas, Tensile Properties of Natural Fiber-Reinforced Epoxy-Hybrid Composites, International Journal of Modern Engineering Research, 2012.
- [35] Md. Rafiquzzaman, S Abdullah and A. M. T. Arifin, Behavioural Observation of Laminated Polymer Composite under Uniaxial Quasi-Static and Cyclic Loads, Fibers and Polymers, 2015.